

Size distribution

F8

Sieve	µm	Specification
1	4000	0
2	2800	≤20
3	2360	≥45
3+4	2000	≥70
5F	1700	≤3

F10

Sieve	µm	Specification
1	3350	0
2	2360	≤20
3	2000	≥45
3+4	1700	≥70
5F	1400	≤3

F12

Sieve	µm	Specification
1	2800	0
2	2000	≤20
3	1700	≥45
3+4	1400	≥70
5F	1180	≤3

F14

Sieve	µm	Specification
1	2360	0
2	1700	≤20
3	1400	≥45
3+4	1180	≥70
5F	1000	≤3

F16

Sieve	µm	Specification
1	2000	0
2	1400	≤20
3	1180	≥45
3+4	1000	≥70
5F	850	≤3

F20

Sieve	µm	Specification
1	1700	0
2	1180	≤20
3	1000	≥45
3+4	850	≥70
5F	710	≤3

F24

Sieve	µm	Specification
1	1180	0
2	850	≤25
3	710	≥45
3+4	600	≥65
5F	500	≤3

F30

Sieve	µm	Specification
1	1000	0
2	710	≤25
3	600	≥45
3+4	500	≥65
5F	425	≤3

F36

Sieve	µm	Specification
1	850	0
2	600	≤25
3	500	≥45
3+4	425	≥65
5F	355	≤3

F46

Sieve	µm	Specification
1	600	0
2	425	≤30
3	355	≥40
3+4	300	≥65
5F	250	≤3

F54

Sieve	µm	Specification
1	500	0
2	355	≤30
3	300	≥40
3+4	250	≥65
5F	212	≤3

F60

Sieve	µm	Specification
1	425	0
2	300	≤30
3	250	≥40
3+4	212	≥65
5F	180	≤3

F70

Sieve	µm	Specification
1	355	0
2	250	≤25
3	212	≥40
3+4	180	≥65
5F	150	≤3

F80

Sieve	µm	Specification
1	300	0
2	212	≤25
3	180	≥40
3+4	150	≥65
5F	125	≤3

F90

Sieve	µm	Specification
1	250	0
2	180	≤20
3	150	≥40
3+4	120	≥65
5F	106	≤3

F100

Sieve	µm	Specification
1	212	0
2	150	≤20
3	125	≥40
3+4	106	≥65
5F	75	≤3

F120

Sieve	µm	Specification
1	180	0
2	125	≤20
3	106	≥45
3+4	90	≥65
5F	63	≤3

F150

Sieve	µm	Specification
1	150	0
2	106	≤15
3	75	≥40
3+4	63	≥65
5F	45	≤3

F180

Sieve	µm	Specification
1	125	0
2	90	≤15
3	63	≥40
3+4	53	≥65

F220

Sieve	µm	Specification
1	106	0
2	75	≤15
3	53	≥40
3+4	45	≥60